

Delglaze® rooflight

Rooflight repairs 10 year guarantee

Preparation

Any rooflights which are perished beyond structural safety should be removed and replaced with new.

Thoroughly clean existing rooflights ensuring they are free from grease, fungus, lichen and mould growth.

Most surfaces do not require priming. Adhesion tests should be carried out on non-standard substrates. If necessary, prime with Sharmans PU primer.

Note: Do not at any time clean the surface with soap detergent. This action would leave a residual film and may adversely affect adhesion.

Before the application of Sharmans products, ensure all surfaces to be treated are dry by using a mechanically driven leaf blower.

Delglaze® 1st Coat

Utilising roller or brush apply a first coat of Delglaze® to the prepared, clean & dry, structurally sound surfaces at a wet film thickness of 166 microns. Allow to cure to a tack free state.

Delglaze® 2nd Coat

Apply a second coat of Delglaze® at a wet film thickness of 166 microns. Allow to fully cure.

The Completed System Dry Film Thickness:

Rooflights: minimum 200 microns

Note: This is an outline specification for the general application of this system. For a bespoke specification to deal with site complexities, please contact us.

Disclaimer: The information, and, in particular, the recommendations relating to the application and end-use of products, are given in good faith based on current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, unless from any written recommendations, or from any other advice offered by HD Sharman. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the Product Data Sheet for the product concerned, copies of which will be supplied on request.

HD Sharman Ltd. T. 01298 812371
High Peak Works F. 01298 812237
Chapel-en-le-Frith E. info@hdsharman.co.uk
High Peak, Derbyshire W. hdsharman.co.uk
SK23 0HW

Application Notes

Delglaze® is supplied ready to use and does not require thinning. The introduction of additional thinning will invalidate the material guarantee.

All surfaces to receive application must be clean and dry. Pay particular attention to the rooflight overlap detail which may be holding trapped water.

Do not apply Delglaze® in inclement weather, or if rain is likely to occur before a tack free cured state is achieved.

Allow each coat to cure until a tack free state is achieved before applying further coats. Curing times will vary with weather conditions. Refer to product data sheet.

Application air temperature must be above 3°C.

Application surface temperature must be 2°C above dew point.

Always allow for expanded sheet profile, when estimating material quantities.

The installing contractor must be fully trained in the use of Sharmans coatings.

It is the contractors' responsibility to inspect each section of the application to ensure the correct measures and steps outlined in this specification document are applied.

Product coverage rates are for guidance purposes only.



sharmans
gutter & roof refurbishment systems